

Technical Data Sheet

Straw All-Weather Montage Foam

All-weather one-component polyurethane foam. Designed for household use. The foam has excellent adhesion to most construction materials: wood, concrete, stone, plastics, metal, etc. It is used to set and lock windows and doors, filling seams and gaps, insulation of pipes and wires, filling voids and holes. It has displays excellent sound and thermal insulation properties.

DIRECTIONS FOR USE:

Before mounting the straw make sure the can temperature is in the range of +10°C to +25°C. Clean the surface from dust and dirt, lightly moisten surface with water. Shake well (at least 20 times). Remove the cap and fasten the plastics tube to the can. Make sure the connection is secure. During application, the can must be kept with the flap side down. Apply foam on 1/2 of the joint width. The uncured foam material, which has not solidified, can be removed with acetone or special cleaner. The foam, which solidified can be removed mechanically only. Use at environmental temperatures ranging from -10°C to +30°C. Store in a cool, dry area and out of reach of children. During storage, avoid direct exposure to sunlight and artificial radiation heaters.

PRECAUTIONARY MEASURES:

Contains: 4,4-diphenylmethane diisocyanate. Harmful in contact with the respiratory system. Irritating to eyes and skin. During application of the foam, it is recommended to use safety glasses, gloves, respiratory protection. In the event of contact with skin or eyes, rinse with water and seek medical advice immediately. Use only in well-ventilated area, Highly flammable material. DO NOT smoke when handling the product. Empty contains must be disposed adequately and must not be punctured or burned.

Shelf life - 12 months from date of manufacture.

The date of manufacture is indicated on the bottle.

TECHNICAL DATA:

NO.	Item	Data
1	Base	Polyurethane
2	Density	17-27 kg/m ³
3	Color	white, light-yellow
4	Skin formation	5-15 minutes
5	Cutting time (30mm bead)	20-40 minutes
6	Curing time	12-24 hours
7	Expansion	30-100%
9	Shelf life	12 months
10	Application temperature	from -10°C to +30°C
11	Temperature resistance	from -50°C to +100°C